

# DATA SHEET

## IMG HDPE 801



Melt Index (190°C/2.16kg) 4.5 D 1238

Density (g/cm<sup>3</sup>) 0.952 D 4883

Deflection Temperature (°F)  
Under Load at 66 psi 160 D 648

Deflection Temperature (°F)  
Under Load at 264 psi 99.1 D 648

Melting Temperature (°F) 271 D 3416

Tensile Strength at Yield (psi) 3570 D 638

Elongation at Break (%) 73 D 638

Flexural Modulus, 1% Secant (psi) 114000 D 790B

ESCR 10% Igpal, F50 (hr) 16.0 D 1693B

Notched Izod Impact Strength,  
ft.lb/in (- 40°F) 1.8 D 256

Recommended Applications: Industrial caps and closures, industrial pails, packaging  
drum lids, recreational vehicle components.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions  
are beyond our control and satisfactory results for this product is the customer's sole responsibility.