

IMG HDPE 804



DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index	8.0	D 1238
Density (g/cm ³)	0.960	D 1505
Izod Impact Strength @ 23°C (ft-lb)	1.4	D 256
Tensile Strength at Yield (psi)	4550	D 638
Hardness, Shore D	72	D 2240
Flexural Modulus (psi)	180	D 790

MARPOL® HDM 508 can - in principle - be used in food contact applications in the USA (FDA) and Canada (HBP). Migration and use limitations may apply.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.