

IMG LLDP 608



DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index 190°C/ 2.16kg (g/10 min)	1.0	D 1238
Density (g/cm ³)	0.919	D 1505
Dart Drop Impact (grams) F50	250-380	D 1709A
Tensile Strength (psi)	MD 1800 TD 1500	D 882
Tear Strength (grams)	MD 4900 TD 3600	D 1922
1% Secant Modulus (psi)	MD 25000 TD 28000	D 882

Additives: No Slip, No Antiblock

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.

